

Plastics — Methods of exposure to laboratory light sources —

Part 2: Xenon-arc lamps

The European Standard EN ISO 4892-2:2006 has the status of a
British Standard

ICS 83.080.01

BSi

National foreword

This British Standard is the official English language version of EN ISO 4892-2:2006. It is identical with ISO 4892-2:2006. It supersedes BS EN ISO 4892-2:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/21, Testing of plastics, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii to iv, pages 1 to 10, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 10 March 2006

© BSI 10 March 2006

ISBN 0 580 47184 5

English Version

Plastics - Methods of exposure to laboratory light sources - Part
2: Xenon-arc lamps (ISO 4892-2:2006)

Plastiques - Méthodes d'exposition à des sources
lumineuses de laboratoire - Partie 2: Lampes à arc au
xénon (ISO 4892-2:2006)

Kunststoffe - Künstliches Bestrahlen oder Bewittern in
Geräten - Teil 2: Xenonbogenlampen (ISO 4892-2:2006)

This European Standard was approved by CEN on 28 October 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN ISO 4892-2:2006

Foreword

This document (EN ISO 4892-2:2006) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2006, and conflicting national standards shall be withdrawn at the latest by August 2006.

This document supersedes EN ISO 4892-2:1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 4892-2:2006 has been approved by CEN as EN ISO 4892-2:2006 without any modifications.

INTERNATIONAL STANDARD

ISO 4892-2

Second edition
2006-02-01

Plastics — Methods of exposure to laboratory light sources —

Part 2: Xenon-arc lamps

*Plastiques — Méthodes d'exposition à des sources lumineuses de
laboratoire —*

Partie 2: Lampes à arc au xénon



Reference number
ISO 4892-2:2006(E)

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Test specimens	6
6 Exposure conditions	6
7 Procedure	8
8 Exposure report	8
Annex A (informative) Filtered xenon-arc radiation — Spectral power distribution	9
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4892-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*.

This second edition cancels and replaces the first edition (ISO 4892-2:1994), which has been technically revised.

ISO 4892 consists of the following parts, under the general title *Plastics — Methods of exposure to laboratory light sources*:

- *Part 1: General guidance*
- *Part 2: Xenon-arc lamps*
- *Part 3: Fluorescent UV lamps*
- *Part 4: Open-flame carbon-arc lamps*

Plastics — Methods of exposure to laboratory light sources —

Part 2: Xenon-arc lamps

1 Scope

This part of ISO 4892 specifies methods for exposing specimens to xenon-arc light in the presence of moisture to reproduce the weathering effects that occur when materials are exposed in actual end-use environments to daylight or to daylight filtered through window glass.

The specimens are exposed to filtered xenon-arc light under controlled conditions (temperature, humidity and/or wetting). Various types of xenon-arc light source and various filter combinations may be used to meet different requirements.

Specimen preparation and evaluation of the results are covered in other International Standards for specific materials.

General guidance is given in ISO 4892-1.

NOTE Xenon-arc exposures of paints and varnishes are described in ISO 11341.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

3 Principle

3.1 A xenon arc, fitted with suitable filters and properly maintained, is used to simulate the spectral power distribution of daylight in the ultraviolet (UV) and visible regions of the spectrum.

3.2 Specimens are exposed to various levels of light, heat, relative humidity and water (see 3.4) under controlled environmental conditions.

3.3 The exposure conditions may be varied by selection of

- a) the light filter(s);
- b) the irradiance level;

- c) the temperature during exposure to light;
- d) the relative humidity in the chamber during light and dark exposures, when exposure conditions requiring control of humidity are used;
- e) the way the test specimens are wetted (see 3.4);
- f) the water temperature and wetting cycle;
- g) the relative lengths of the light and dark periods.

3.4 Wetting is usually produced by spraying the test specimens with demineralized/deionized water, by immersion in water or by condensation of water vapour onto the surfaces of the specimens.

3.5 The procedure may include measurements of the irradiance and radiant exposure in the plane of the specimens.

3.6 It is recommended that a similar material of known performance (a control) be exposed simultaneously with the test specimens to provide a standard for comparative purposes.

3.7 Intercomparison of results obtained from specimens exposed in different apparatus should not be made unless an appropriate statistical relationship has been established between the apparatuses for the particular material exposed.

4 Apparatus

4.1 Laboratory light source

4.1.1 General

The light source shall comprise one or more quartz-jacketed xenon-arc lamps which emit radiation from below 270 nm in the ultraviolet through the visible spectrum and into the infrared. In order to simulate daylight, filters shall be used to remove short-wavelength UV radiation (method A, see Table 1). Filters to minimize irradiance at wavelengths shorter than 310 nm shall be used to simulate daylight through window glass (method B, see Table 2). In addition, filters to remove infrared radiation may be used to prevent unrealistic heating of the test specimens, which can cause thermal degradation not experienced during outdoor exposures.

NOTE Solar spectral irradiance for a number of different atmospheric conditions is described in CIE Publication No. 85. The benchmark daylight used in this part of ISO 4892 is that defined in Table 4 in CIE No. 85:1989.

4.1.2 Spectral irradiance of xenon-arc lamps with daylight filters

Filters are used to filter xenon-arc emissions in order to simulate daylight (CIE Publication No. 85:1989, Table 4). The minimum and maximum levels of the relative spectral irradiance in the UV wavelength range are given in Table 1 (see also Annex A).

Table 1 — Relative spectral irradiance of xenon-arc lamps with daylight filters ^{a, b} (method A)

Spectral passband (λ = wavelength in nm)	Minimum ^c %	CIE No. 85:1989, Table 4 ^{d, e} %	Maximum ^c %
$\lambda < 290$			0,15
$290 \leq \lambda \leq 320$	2,6	5,4	7,9
$320 < \lambda \leq 360$	28,2	38,2	39,8
$360 < \lambda \leq 400$	54,2	56,4	67,5

^a This table gives the irradiance in the given passband, expressed as a percentage of the total irradiance between 290 nm and 400 nm. To determine whether a specific filter or set of filters for a xenon-arc lamp meets the requirements of this table, the spectral irradiance must be measured from 250 nm to 400 nm. The total irradiance in each wavelength passband is then summed and divided by the total irradiance from 290 nm to 400 nm.

^b The minimum and maximum limits in this table are based on more than 100 spectral irradiance measurements with water- and air-cooled xenon-arc lamps with daylight filters from different production lots and of various ages ^[3], used in accordance with the recommendations of the manufacturer. As more spectral irradiance data become available, minor changes in the limits are possible. The minimum and maximum limits are at least three sigma from the mean for all the measurements.

^c The minimum and maximum columns will not necessarily sum to 100 % because they represent the minima and maxima for the measurement data used. For any individual spectral irradiance, the percentages calculated for the passbands in this table will sum to 100 %. For any individual xenon-arc lamp with daylight filters, the calculated percentage in each passband shall fall within the minimum and maximum limits given. Exposure results can be expected to differ if obtained using xenon-arc apparatus in which the spectral irradiances differ by as much as that allowed by the tolerances. Contact the manufacturer of the xenon-arc apparatus for specific spectral irradiance data for the xenon-arc lamp and filters used.

^d The data from Table 4 in CIE Publication No. 85:1989 is the global solar irradiance on a horizontal surface for an air mass of 1,0, an ozone column of 0,34 cm at STP, 1,42 cm of precipitable water vapour and a spectral optical depth of aerosol extinction of 0,1 at 500 nm. These data are target values for xenon-arc lamps with daylight filters.

^e For the solar spectrum represented by Table 4 in CIE No. 85:1989, the UV irradiance (between 290 nm and 400 nm) is 11 % and the visible irradiance (between 400 nm and 800 nm) is 89 %, expressed as a percentage of the total irradiance between 290 nm and 800 nm. The percentage of the UV irradiance and that of the visible irradiance incident on specimens exposed in xenon-arc apparatus may vary due to the number of specimens being exposed and their reflectance properties.

4.1.3 Spectral irradiance of xenon-arc lamps with window glass filters

Filters are used to filter the xenon-arc lamp emissions in order to simulate daylight which has passed through window glass. The minimum and maximum levels of the relative spectral irradiance in the UV region are given in Table 2 (see also Annex A).

Table 2 — Relative spectral irradiance for xenon-arc lamps with window glass filters ^{a, b} (method B)

Spectral passband (λ = wavelength in nm)	Minimum ^c %	CIE No. 85:1989, Table 4 plus effect of window glass ^{d, e} %	Maximum ^c %
$\lambda < 300$			0,29
$300 \leq \lambda \leq 320$	0,1	≤ 1	2,8
$320 < \lambda \leq 360$	23,8	33,1	35,5
$360 < \lambda \leq 400$	62,4	66,0	76,2

^a This table gives the irradiance in the given passband, expressed as a percentage of the total irradiance between 290 nm and 400 nm. To determine whether a specific filter or set of filters for a xenon-arc lamp meets the requirements of this table, the spectral irradiance must be measured from 250 nm to 400 nm. The total irradiance in each passband is then summed and divided by the total irradiance between 290 nm and 400 nm.

^b The minimum and maximum limits in this table are based on more than 30 spectral irradiance measurements with water- and air-cooled xenon-arc lamps with window glass filters from different production lots and of various ages ^[3], used in accordance with the recommendations of the manufacturer. As more spectral irradiance data become available, minor changes in the limits are possible. The minimum and maximum limits are at least three sigma from the mean for all the measurements.

^c The minimum and maximum columns will not necessarily sum to 100 % because they represent the minima and maxima for the data used. For any individual spectral irradiance, the percentages calculated for the passbands in this table will sum to 100 %. For any individual xenon-arc lamp with window glass filters, the calculated percentage in each passband shall fall within the minimum and maximum limits given. Exposure results can be expected to differ if obtained using xenon-arc apparatus in which the spectral irradiances differ by as much as that allowed by the tolerances. Contact the manufacturer of the xenon-arc apparatus for specific spectral irradiance data for the xenon-arc lamp and filters used.

^d The data from Table 4 in CIE No. 85:1989 plus the effect of window glass was determined by multiplying the CIE No. 85:1989, Table 4, data by the spectral transmittance of 3-mm-thick window glass (see ISO 11341). These data are target values for xenon-arc lamps with window glass filters.

^e For the CIE No. 85:1989 plus window glass data, the UV irradiance between 300 nm and 400 nm is typically about 9 % and the visible irradiance (between 400 nm and 800 nm) is typically about 91 %, expressed as a percentage of the total irradiance between 300 nm and 800 nm. The percentage of the UV irradiance and that of the visible irradiance incident on specimens exposed in xenon-arc apparatus may vary due to the number of specimens being exposed and their reflectance properties.

4.1.4 Irradiance uniformity

The irradiance at any position in the area used for specimen exposure shall be at least 80 % of the maximum irradiance. Requirements for periodic repositioning of specimens when this requirement is not met are described in ISO 4892-1.

NOTE For some materials of high reflectivity, periodic repositioning of specimens is recommended to ensure uniformity of exposures, even when the irradiance uniformity in the exposure area is within the limits so that repositioning is not required.

4.2 Test chamber

The design of the test chamber may vary, but it shall be constructed from inert material. In addition to the controlled irradiance, the test chamber shall provide for control of temperature. For exposures that require control of humidity, the test chamber shall include humidity-control facilities that meet the requirements of ISO 4892-1. When required by the exposure used, the apparatus shall also include facilities for the provision of water spray or the formation of condensate on the surface of the test specimens, or for the immersion of the specimens in water. Water used for water spray shall meet the requirements of ISO 4892-1.

The light source(s) shall be located, with respect to the specimens, such that the irradiance at the specimen surface complies with 6.1.

NOTE If the lamp system (one or more lamps) is centrally positioned in the chamber, the effect of any eccentricity of the lamp(s) on the uniformity of exposure may be reduced by using a rotating frame carrying the specimens or by repositioning or rotating the lamps.

Should any ozone be generated from operation of the lamp(s), the lamp(s) shall be isolated from the test specimens and operating personnel. If the ozone is in an air stream, it shall be vented directly to the outside of the building.

4.3 Radiometer

When a radiometer is used, it shall comply with the requirements outlined in ISO 4892-1.

4.4 Black-standard/black-panel thermometer

The black-standard or black-panel thermometer used shall comply with the requirements for these devices given in ISO 4892-1.

4.5 Wetting and humidity-control equipment

4.5.1 General

Specimens may be exposed to moisture in the form of water spray or condensation, or by immersion. Specific exposure conditions using water spray are described in Table 3. If condensation, immersion or other methods are used to expose the specimens to moisture, details of the procedures and exposure conditions used shall be included in the exposure report.

Table 3 also describes exposure conditions in which the relative humidity is controlled as well as those in which humidity control is not required.

NOTE The relative humidity of the air can have a significant influence on the photodegradation of polymers.

4.5.2 Relative-humidity control equipment

For exposures where relative-humidity control is required, the location of the sensors used to measure the humidity shall be as specified in ISO 4892-1.

4.5.3 Spray system

The test chamber shall be equipped with a means of directing an intermittent water spray onto the fronts or backs of the test specimens under specified conditions. The spray shall be uniformly distributed over the specimens. The spray system shall be made from corrosion-resistant materials that do not contaminate the water employed.

The water sprayed onto the specimen surfaces shall have a conductivity below 5 $\mu\text{S}/\text{cm}$, contain less than 1 $\mu\text{g}/\text{g}$ dissolved solids and leave no observable stains or deposits on the specimens. Care shall be taken to keep silica levels below 0,2 $\mu\text{g}/\text{g}$. A combination of deionization and reverse osmosis can be used to produce water of the desired quality.

4.6 Specimen holders

Specimen holders may be in the form of an open frame, leaving the backs of the specimens exposed, or they may provide the specimens with a solid backing. They shall be made from inert materials that will not affect the results of the exposure, for example non-oxidizing alloys of aluminium or stainless steel. Brass, steel or copper shall not be used in the vicinity of the test specimens. The backing used may affect the results, as may any space between the backing and the test specimen, particularly with transparent specimens, and shall be agreed on between the interested parties.

4.7 Apparatus to assess changes in properties

The apparatus required by the International Standards relating to the determination of the properties chosen for monitoring (see also ISO 4582) shall be used.

5 Test specimens

Refer to ISO 4892-1.

6 Exposure conditions

6.1 Radiation

Unless otherwise specified, control the irradiance at the levels indicated in Table 3. Other irradiance levels may be used when agreed on by the interested parties. The irradiance, and the passband in which it was measured, shall be included in the exposure report.

6.2 Temperature

6.2.1 Black-standard/black-panel temperature

For referee purposes, Table 3 specifies black-standard temperatures. For normal work, black-panel thermometers may be used in place of black-standard thermometers. However, allowance will have to be made for the fact that the two types of thermometer indicate different temperatures, due to their different thermal conductivities (see ISO 4892-1).

NOTE 1 If a black-panel thermometer is used, the temperature indicated will be 3 °C to 12 °C lower than that indicated by a black-standard thermometer under typical exposure conditions.

If a black-panel thermometer is used, then the panel material, the type of temperature sensor and the way in which the sensor is mounted on the panel shall be included in the exposure report.

NOTE 2 If higher temperatures (see cycles 3, 4 7 and 8 in Table 3) are used for special exposures, the tendency for specimens to undergo thermal degradation will increase and this may affect the results of such exposures.

Other temperatures may be used when agreed on by the interested parties, but shall be stated in the exposure report.

If water spray is used, the temperature requirements apply to the end of the dry period. If the thermometer does not reach a steady state during the short water-spray part of the cycle, the temperature specified shall be established without water spray and the maximum temperature attained during the dry part of the cycle shall be reported.

NOTE 3 The additional measurement of a white-standard/white-panel temperature with a white-standard/white-panel thermometer according to ISO 4892-1 gives important information on the range of surface temperatures of differently coloured test specimens.

6.2.2 Chamber air temperature

Exposures can be run either with the chamber air temperature controlled at a specified level or allowing the air temperature to find its own level (see Table 3).

6.3 Relative humidity of chamber air

Exposures can be conducted either with the relative humidity controlled at a specified level or allowing the relative humidity to find its own level (see Table 3).

Table 3 — Exposure cycles

Method A — Exposures using daylight filters (artificial weathering)						
Cycle No.	Exposure period	Irradiance ^a		Black-standard temperature °C	Chamber temperature °C	Relative humidity %
		Broadband (300 nm to 400 nm) W/m ²	Narrowband (340 nm) W/(m ² .nm)			
1	102 min dry	60 ± 2	0,51 ± 0,02	65 ± 3	38 ± 3	50 ± 10 ^b
	18 min water spray	60 ± 2	0,51 ± 0,02	—	—	—
2	102 min dry	60 ± 2	0,51 ± 0,02	65 ± 3	Not controlled	Not controlled
	18 min water spray	60 ± 2	0,51 ± 0,02	—	—	—
3	102 min dry	60 ± 2	0,51 ± 0,02	100 ± 3	65 ± 3	20 ± 10
	18 min water spray	60 ± 2	0,51 ± 0,02	—	—	—
4	102 min dry	60 ± 2	0,51 ± 0,02	100 ± 3	Not controlled	Not controlled
	18 min water spray	60 ± 2	0,51 ± 0,02	—	—	—
Method B — Exposures using window glass filters						
Cycle No.	Exposure period	Irradiance ^a		Black-standard temperature °C	Chamber temperature °C	Relative humidity %
		Broadband (300 nm to 400 nm) W/m ²	Narrowband (420 nm) W/(m ² .nm)			
5	Continuously dry	50 ± 2	1,10 ± 0,02	65 ± 3	38 ± 3	50 ± 10 ^b
6	Continuously dry	50 ± 2	1,10 ± 0,02	65 ± 3	Not controlled	Not controlled
7	Continuously dry	50 ± 2	1,10 ± 0,02	100 ± 3	65 ± 3	20 ± 10
8	Continuously dry	50 ± 2	1,10 ± 0,02	100 ± 3	Not controlled	Not controlled
NOTE The ± tolerances given for irradiance, black-standard temperature and relative humidity are the allowable fluctuations of the parameter concerned about the given value under equilibrium conditions. This does not mean that the value can vary by plus/minus the amount indicated from the given value.						
^a The irradiance values given are those that have historically been used. In apparatus capable of producing higher irradiances, the actual irradiance may be significantly higher than the stated values, e.g. up to 180 W/m ² (300 nm to 400 nm) for xenon-arc lamps with daylight filters or 162 W/m ² (300 nm to 400 nm) for xenon-arc lamps with window glass filters.						
^b For materials sensitive to humidity, the use of (65 ± 10) % RH is recommended.						

6.4 Spray cycle

The spray cycle used shall be as agreed between the interested parties, but should preferably be that in Table 3, method A.

6.5 Cycles with dark periods

The conditions in Table 3 are valid for continuous presence of radiant energy from the source. More complex cycles may be used. These could include dark periods that might involve high humidity and/or the formation of condensate on the surfaces of the specimens.

Such programmes shall be given, with full details of the conditions, in the exposure report.

6.6 Sets of exposure conditions

Table 3 lists various sets of conditions for exposures conducted with daylight filters (method A) and those conducted with window glass filters (method B).

If no other exposure conditions are specified, use cycle No. 1.

7 Procedure

7.1 General

It is recommended that at least three test specimens of each material evaluated be exposed in each run to allow statistical evaluation of the results.

7.2 Mounting the test specimens

Attach the specimens to the specimen holders in the equipment in such a manner that the specimens are not subject to any applied stress. Identify each test specimen by suitable indelible marking, avoiding areas to be used for subsequent testing. As a check, a plan of the test-specimen positions may be made.

If desired, in the case of specimens used to determine change in colour and appearance, a portion of each test specimen may be shielded by an opaque cover throughout the exposure. This gives an unexposed area adjacent to the exposed area for comparison. This is useful for checking the progress of the exposure, but the data reported shall always be based on a comparison with file specimens stored in the dark.

7.3 Exposure

Before placing the specimens in the test chamber, be sure that the apparatus is operating under the desired conditions (see Clause 6). Programme the apparatus with the selected conditions to operate continuously for the required number of cycles at the selected exposure conditions. Maintain these conditions throughout the exposure, keeping any interruptions to service the apparatus and to inspect the specimens to a minimum.

Expose the test specimens and, if used, the irradiance-measuring instrument for the specified period. Repositioning of the specimens during exposure is desirable and may be necessary. Follow the guidance in ISO 4892-1.

If it is necessary to remove a test specimen for periodic inspection, take care not to touch the exposed surface or alter it in any way. After inspection, return the specimen to its holder or to its place in the test chamber with its exposed surface oriented in the same direction as before.

7.4 Measurement of radiant exposure

If used, mount the radiometer so that it measures the irradiance at the exposed surface of the test specimen.

When radiant exposures are used, express the exposure interval in terms of incident radiant energy per unit area of the exposure plane, in joules per square metre (J/m^2), in the wavelength band from 300 nm to 400 nm or in joules per square metre per nanometre [$J/(m^2 \cdot nm)$] at the wavelength selected (e.g. 340 nm).

7.5 Determination of changes in properties after exposure

These shall be determined as specified in ISO 4582.

8 Exposure report

Refer to ISO 4892-1.

Annex A (informative)

Filtered xenon-arc radiation — Spectral power distribution

A.1 General

CIE Publication No. 85:1989 provides data on spectral solar irradiance for typical atmospheric conditions and this data can be used as a basis for comparing laboratory light sources with daylight. The data used for filtered xenon-arc radiation are given in Table 4 in CIE No. 85:1989.

A.2 Spectral irradiance specification (UV region)

A.2.1 Xenon-arc lamps with daylight filters

The data given in CIE Publication No. 85:1989, Table 4, for the UV region (< 400 nm) represent the irradiance benchmark for xenon-arc lamps with daylight filters. Table 1 gives the CIE No. 85:1989, Table 4, benchmark data.

A.2.2 Xenon-arc lamps with window glass filters

The benchmark spectral data for xenon-arc lamps with window glass filters given in Table 2 were determined by modifying the data in the UV region given in CIE Publication No. 85:1989, Table 4, to allow for the transmission of typical window glass. The window glass transmittance used was based on the transmittance of 3-mm-thick window glass as given in Table B.2 of ISO 11341:2004. The CIE Publication No. 85:1989, Table 4, irradiance was multiplied by the appropriate transmittance of the window glass to determine the irradiance in each passband.

A.2.3 Specification limits

The spectral irradiance specifications given in Tables 1 and 2 are based on spectral irradiance data provided by 3M, Atlas Material Testing Technology, Q-Panel Lab Products, and Suga Test Instruments. The irradiance in each passband was totaled and then expressed as a percentage of the total irradiance between 290 nm and 400 nm. The specification limits given in Tables 1 and 2 are based on plus and minus 3 standard deviations from the mean of the data available. Assuming that the measurements are representative of the xenon-arc apparatus population, this range encompasses 99 % of this population.

Bibliography

- [1] CIE Publication No. 85:1989, *Solar spectral irradiance*
- [2] ISO 11341:2004, *Paints and varnishes — Artificial weathering and exposure to artificial radiation — Exposure to filtered xenon-arc radiation*
- [3] ASTM G 155, *Standard Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.